

## Abstract

The invention relates to a pressure sensitive adhesive composition containing an acrylic polymer having a weight average molecular weight of 300,000 or higher and produced by copolymerizing: a C<sub>1-14</sub> alkyl (meth)acrylate; 0.2 to 1.8 phr of an ethylenic monomer having a cyclic ether group; and 4 to 8 phr of a polymerizable unsaturated carboxylic acid